

Hysteresis in cycling through first-order phase transitions in vortex matter, akin to the well-studied phenomenon of supercooling of water, has been discussed in literature. Hysteresis can be seen while varying either temperature T or magnetic field H (and thus the density of vortices). Our recent work on phase transitions with two control variables shows that the observable region of metastability of the supercooled phase would depend on the path followed in H - T space, and will be larger when T is lowered at constant H compared to the case when H is lowered at constant T . We discuss the effect of isothermal field variations on metastable supercooled states produced by field-cooling. This path dependence is not *a priori* applicable to metastability caused by reduced diffusivity or hindered kinetics.

Keywords Supercooling, metastability, superconductors, vortex matter, first-order transition.

64.60 My; 64.70 Dv; 74.60.-w

Supercooling across first-order phase transitions in vortex matter

P. Chaddah and S. B. Roy
Low Temperature Physics Lab
Centre for Advanced Technology,
Indore 452013, India
 (February 1, 2008)

In recent years first-order phase transitions in vortex matter have been studied with both temperature and magnetic field (or vortex density) as the control variable, and the question of metastability has been addressed [1–3]. The phase transition temperature $T_C(H)$ [4] drops as magnetic field is raised, as depicted in Fig.1. Vortex matter contracts on being heated from the ordered (solid) phase to the disordered (liquid) phase, similar to the behaviour of ice at pressures below 200 MPa [5]. Hysteresis has been reported, with both field and temperature as the control variable, across the vortex-lattice-melting transition [1,2]. We have also reported supercooling of the higher entropy vortex-solid phase in the polycrystalline samples of C15 Laves phase superconductor CeRu_2 , both on reducing field and on reducing temperature, and have found that the supercooled state persists farther in the latter case [3,6]. Similar signatures of supercooling have been reported in single crystals of CeRu_2 , NbSe_2 and $\text{YBa}_2\text{Cu}_3\text{O}_7$ [7–9].

The standard treatment [10] of supercooling across a first-order transition considers that only temperature is varied and other possible control variables (like magnetic field) are held constant. The free-energy density is expressed in terms of the order parameter S as

$$f(T, S) = (r/2)S^2 - wS^3 + uS^4 \quad (1)$$

where w and u are positive and temperature-independent [10]. (We will assume in this paper that symmetry does not prohibit terms of odd order. If it does, then the free energy would be expressed as $f = (r/2)S^2 - wS^4 + uS^6$, and it is easy to follow and carry through all arguments in this paper. The assumption of the form of equation (1) is thus made without loss of generality.) At $T = T_C$ the two stable states with $f = 0$, are at $S = 0$ and at $S = S_C = w/(2u)$. These are separated by an energy barrier peaking at $S = S_B = w/(4u)$, of height $f_B = w^4/(256 u^3)$. These results are independent of any assumption about the detailed temperature dependence of $r(T)$. The standard treatment [10] assumes that $r(T) = a [T - T^*]$, where a is positive and temperature independent, and where d^2f/dS^2 at $S=0$ vanishes at $T = T^*$. Simple algebra shows that the limit of metastability on cooling is reached at $T^* = T_C - w^2/(2ua)$. The limit of metastability on heating is reached when the ordered state no longer has a local minimum in $f(S)$. This occurs at $T^{**} = T_C + w^2/(16ua)$. As noted above, supercooling (or superheating) can persist till T^* (or T^{**}) only in the limit of infinitesimal fluctuations. The barrier height around $S=0$ drops continuously as T is lowered below T_C , and this is depicted in Fig.2. In the presence of a fluctuation of energy e_f , supercooling will terminate at T_0 where the energy barrier satisfies

$$f_B(T_0) \approx [e_f + k_B T_0] \quad (2)$$

Similarly, the barrier height around the ordered state drops continuously to zero as T is raised towards T^{**} , and this is depicted in Fig.3. The fluctuation energy in the ordered state will dictate when superheating will terminate.

The formulation stated above is of course valid for a first order transition in vortex-matter as a function of T .

Vortex-matter phase transitions are encountered in H - T space and the limit of supercooling (T^*) is now a function of H . This standard treatment has recently been extended to the case where one has two control variables, viz. density and temperature. It has been shown [11] that when T_C falls with rising density (as in water-ice below 200 MPa), then T_C - T^* will rise with rising density. If, on the other hand, T_C rises with rising density (as in water-ice above 200 MPa), then T_C - T^* will fall with rising density. This appears consistent with experiments on ice (see Fig.5 of [5]). The density of vortices rises with increasing H , and these predictions are also consistent with our data on single crystal CeRu_2 [12]. The first order phase boundary $T_C(H)$ can be crossed by following arbitrary paths in H - T space. It has been argued, however, that the very procedure of varying H introduces fluctuations, so that the disordered phase can be supercooled up to $T^*(H)$ only if T is lowered in constant H (i.e. in the field-cooled mode); fluctuations will terminate supercooling at a line $T_0(H)$ which lies above the $T^*(H)$ line [11]. For the case where H is lowered isothermally to cross $T_C(H)$, it has been argued [11] that the $T_0(H)$ line will be such that $T_0(H)$ - $T^*(H)$ rises with rising H .

In this paper, we wish to consider the case where the sample is cooled in constant H to a temperature T satisfying $T^*(H) < T < T_C(H)$, and then subjected to an isothermal field variation. The isothermal field variation ΔH produces a fluctuation energy e_f which increases monotonically (but nonlinearly) with ΔH [11]. The field-cooled state at T corresponds to supercooling of the disordered phase, and it sits in a local minimum of free-energy as depicted in Fig.2(b) and 2(c). The fluctuation energy e_f (and thus the isothermal field variations, ΔH) required to cross-over to

the absolute minimum in free energy (the ordered state) is clearly less at T_2 than at T_1 because T_2 is closer to T^* and the free energy barrier f_B defining the local minimum is smaller. Similarly one can field-cool to (H_1, T_2) and (H_2, T_2) , with H_2 less than H_1 and $T_2(H_2)$ greater than $T^*(H_2)$ as depicted schemetically in Fig.1. Since the point (H_2, T_2) lies closer to $T^*(H)$ line, it follows immediately that the free energy barrier f_B separating the disordered metastable state from the globally ordered state will be smaller at (H_2, T_2) than at (H_1, T_2) . The fluctuation energy e_f , and thus the isothermal field variation, ΔH , required to cause the metastable state to transform to the ordered state will be smaller at H_2 than at H_1 . Our heuristic arguments can similarly be used for various other experimentally accessible paths in (H, T) space.

We have argued that an extension [11] of the standard theory of supercooling can explain various path-dependent history effects seen in first-order phase transitions in vortex matter. We recognize, however, that metastability does not necessarily imply a first order transition (a sudden change in an equilibrium property like volume does). Metastability is also associated with glassy systems which have been "frozen out of equilibrium". We contrast these two types of metastabilities by considering a liquid-solid transition. A liquid can be supercooled below its melting point T_m without any sudden change in its diffusivity. A glass, on the other hand, is obtained by cooling a liquid very rapidly. The atoms freeze into an amorphous structure corresponding to the liquid. A glass is thus a supercooled liquid that has been frozen out of equilibrium [13]. Its diffusivity dropped (and viscosity rose to a value greater than 10^{13} poise) before the atoms could rearrange themselves from the structure of a liquid to that of a crystal.

A supercooled liquid is thus distinct from a glass in that its diffusivity is large enough to permit it to explore configuration space on laboratory timescales, such that the ergodic hypothesis is valid. Entropy is a valid concept, free energy can be defined, and a supercooled liquid is in a local minimum of free energy. A glass, on the other hand, explores only its immediate neighbourhood in configuration space, is non-ergodic, and is in a local minimum only of the energy landscape [13] and not of the free energy. A glass is characterised by low diffusivity and hindered kinetics, whereas a supercooled liquid is understood by conventional statistical mechanics. Finally, it is not necessary that a glass be associated with an underlying thermodynamic singularity (i.e., a first order phase transition) [14].

We have in this paper made definite predictions on the path dependences when metastabilities are associated with supercooling across a first order transition. These predictions do not, *a priori*, apply to metastabilities caused by hindered kinetics associated with a glass. In fact, naive arguments using hindered kinetics suggest that since the extent of vortex motion is more in isothermal field scans [15], this path would show more persistent metastabilities than the field-cooled path. Supercooling in the case of isothermal field reduction would then persist farther than in the case of cooling in constant field, contrary to our predictions [11] for supercooling across first order transitions. The path-dependence of metastabilities associated with hindered kinetics thus needs to be quantified, beyond these naive arguments.

We gratefully acknowledge helpful discussions with Dr. S. M. Sharma, Dr. S. K. Sikka, Dr. Srikanth Sastry, Prof. Deepak Dhar and Dr. Sujeet Chaudhary.

-
- [1] D. E. Farrell in Physical Properties of High Temperature Superconductor IV , p7, Ed. D. M. Ginsberg (World Scientific 1994).
 - [2] J. A. Fendrich, G. W. Crabtree, W. K. Kwok, U. Welp, and B. Veal , in The Superconducting State in Magnetic Fields, p41, Ed. C. A. R. Sa de Melo (World Scientific, 1998).
 - [3] S. B. Roy and P. Chaddah, Physica **C279** 70 (1997); P. Chaddah and S. B. Roy, Bull. Mat. Sci. **22** 275 (1999).
 - [4] T_C refers to a phase transition within vortex matter, and not to the superconducting to normal transition. This can correspond to vortex-lattice melting [1,2], or to a transition between two states with pinning [3].
 - [5] H.E. Stanley, Pramana-J. Phys. **53** 53 (1999).
 - [6] S. B. Roy and P. Chaddah, J. Phy. Cond. Matter **9** L625 (1997); S. B. Roy et al, J. Phy. Cond. Matter **10** 4885 (1998); S. B. Roy et al, J. Phy. Cond. Matter **10** 8327 (1998).
 - [7] S. Chaudhary, S.B. Roy and P. Chaddah, Invited Talk at LT22 Conference, Finland, August 1999 (to be published in a special issue of Physica **B**).
 - [8] G. Ravikumar et al, Phys. Rev. **B57** 11069 (1998).
 - [9] S. Kokaliaris et al, Phys. Rev. Lett. **82** 5116 (1999).
 - [10] P. M. Chaikin and T. C. Lubensky, Principles of Condensed Matter Physics (Cambridge University Press, 1995) Chapter 4.
 - [11] P. Chaddah and S.B. Roy, Phys. Rev. **B60** (1999), scheduled for Nov. 1 issue.
 - [12] S. Chaudhary et al, to be published.

- [13] F.H. Stillinger, Science **267** 1935 (1995).
- [14] P.G. Debenedetti, Metastable Liquids (Princeton University Press, 1996) Chapter 4.
- [15] M. Steingart, A.G. Putz and E.J. Kramer, J. Appl. Phys. **64** 5580 (1973).

FIG. 1. We show a schematic of the phase transition line $T_C(H)$ and the stability limit $T^*(H)$ for the supercooled state : (H_1, T_1) and (H_1, T_2) indicate supercooled states when vortex matter is cooled in a field H_1 . See text for details.

FIG. 2. We show schematic free energy curves for (a) $T=T_C$, (b) $T=T_1 < T_C$, (c) $T=T_2 < T_1$ and (d) $T=T^*$. The disordered state sits in a local minimum and is stable against infinitesimal fluctuations for $T > T^*$. This local minimum becomes shallower as T is lowered below T_C and the disordered state at T_2 is unstable to a smaller fluctuation energy than at T_1 .

FIG. 3. We show schematic free energy curves for (a) $T=T_3 > T_C$, (b) $T=T_4 > T_3$ and (c) $T=T^{**}$. The ordered state sits in a local minimum and is stable against infinitesimal fluctuations for $T < T^{**}$.





